

DESCRIPTION			
Backing		NT	MK
Thickness		2.25 ± 0.15 mm 0.088 ± 0.006"	6.20 ± 0.30 mm 0.244 ± 0.012"
Weight		2.20 ± 0.15 kg/m <sup>2</sup> 4.05 lb/Sq.Yd	4.32 ± 0.25 kg/m <sup>2</sup> 8 lb/Sq.Yd
Roll width		200 cm 6.56'	196 cm 6.43'
Roll length		24 lm 78.72'	15 lm 49.21'
PERFORMANCE			
Dimensional stability	ASTM D 1204	≤ 0.3 %	
Abrasion resistance	ISO 9352 TABER TEST	300 ± 50 mg < 0.01 oz	< 300 mg < 0.01 oz
Indentation resistance	ISO 24343-1	≤ 0.2 mm < 0.008"	≤ 1.0 mm < 0.04"
Low temperature resistance	D 42 1235 A	- 20°C / -4°F	- 25°C / -13°F
Sound Damping Characteristics	ISO 717/2	ΔI > 4 dB	ΔI > 10 dB
Color fastness	ASTM D 4459	≥ 6	
Slip resistance	ASTM D 2047	> 0.6	
Fire resistance	FMVSS 302 (ISO 3795/76)	Conform	
	Docket 90a (ASTM E648) (NFPA 253)	Class 1 (CRF > 0.45 W/cm <sup>2</sup> )	
Resistance to chemicals	ISO 26987	Unaffected by diluted acids and bases Unaffected by domestic products (excluding solvents for plasticized PVC)	